



DASAR 76 METAL PRIMER

DASAR 76 METAL PRIMER is formulated for industrial needs and household purposes. This coating offers excellent long term protection to steel but may also be used as a permanent primer to protect steel during field erection and in weather exposed storage. DASAR 76 METAL PRIMER successfully resist the influence of light, industrial atmospheres, acids, alkalis and severest weather conditions.

TYPE	Alkyd Modified
GLOSS	Semi-gloss
SPREADING RATE	6 - 8 m ² /kg
TOTAL SOLIDS CONTENT(VOL. %)	Approx. 90
SPECIFIC GRAVITY	1.28
DRYING TIME	1 – 2 hours
THINNER	Trisula Synthetic Thinner
METHOD OF APPLICATION	Brush, roller or spray
PRE-TREATMENT	Cleaning * The surface must be cleaned from rust, mill scale, oil and grease before applying primer * (Oil, grease and dirt can be removed easily with Thinner A Special. For best results, primer should be applied directly after cleaning operation)
FINISH	ALTEX SYNTHETIC SUPER, ALTEX SYNTHETIC
ATTENTION	* The work should be carried out on dry surfaces. * Best results can be obtained when applied over sandblasted steel.

PT. Atlantic Ocean Paint
031-51203009 / 031- 99008814
info@atlanticoceanpaint.com
www.atlanticoceanpaint.com
@atlanticoceanpaint

