

## Technical Data Sheet Solventbased

Document #: TDS-02 / SB / 0015

Version : 001

Issued Date: 10/10/2019



## NEPTUNE ZINC CHROMATE

NEPTUNE ZINC CHROMATE, is formulated for industrial needs and household purposes. This coating offers excellent long term protection to steel, but may also be used as permanent primer to protect steel during field erection and in weather exposed storage. NEPTUNE ZINC CHROMATE using alkyd resin and ZnCrO3 as a rust preventive pigment. NEPTUNE ZINC CHROMATE successfully resist the influence of light, industrial atmospheres, mildacids /alkalis and severe weather condition.

ТҮРЕ	Alkyd Modified
GLOSS	Semi-gloss
SPREADING RATE	8 - 10 m²/ kg, ±50μ dft
TOTAL SOLIDS CONTENT(VOL. %)	<u>+</u> 88.5 %
SPECIFIC GRAVITY	1.49
DRYING TIME	Approx. 60 min.
THINNER	Trisula Synthetic Thinner
METHOD OF APPLICATION	Spray or brush
PRE-TREATMENT	Surface must be cleaned from rust, mill scale, oil and grease.
ATTENTION	The work should be carried out on dry surface.

PT. Atlantic Ocean Paint 031-51203009 / 031- 99008814 info@atlanticoceanpaint.com www.atlanticoceanpaint.com



